

FASTLIFT SPECIFICATIONS FOR 3-STRAND ROPES

DIAMETER (mm)		10	12	16	20	24	REMARKS
MANILA GRADE 1	BREAKING LOAD	710kg	1070kg	2030kg	3230kg	4570kg	HIGH ABRASION RESISTANCE
	APPROX. METRES PER 50kg	-	500	275	190	135	HIGH MOISTURE ABSORPTION
	APPROX. METRES PER 25kg	358	250	138	95	-	LOW ACID RESISTANCE
NYLON	BREAKING LOAD	2080kg	3000kg	5300kg	8300kg	12000kg	HIGH ABRASION RESISTANCE
	APPROX. METRES PER 50kg	-	-	315	210	140	LOW MOISTURE ABSORPTION
	APPROX. METRES PER 25kg	365	253	158	-	-	RESISTANT TO MOST ACIDS
SISAL	BREAKING LOAD	635kg	955kg	1805kg	2845kg	4065kg	HIGH ABRASION RESISTANCE
	APPROX. METRES PER 50kg	-	460	255	185	118	HIGH MOISTURE ABSORPTION
	APPROX. METRES PER 25kg	365	230	127	-	-	LOW ACID RESISTANCE
POLYPROPYLENE	BREAKING LOAD	1425kg	2030kg	3500kg	5370kg	7600kg	HIGH ABRASION RESISTANCE
	APPROX. METRES PER 50kg	-	-	430	250	185	NIL MOISTURE ABSORPTION
	APPROX. METRES PER 25kg	545	353	215	-	-	RESISTANT TO MOST ACIDS

SPECIFICATIONS ON DIAMETERS NOT SHOWN ABOVE ARE AVAILABLE ON REQUEST